for enhanced search functionality please visit UL's iQ<sup>™</sup> family of databases

**Component - Plastics** 

```
E107536
```

## SHINKONG SYNTHETIC FIBERS CORP

223 YEN PING RD SEC 3, PIN CHENG TAOYUAN HSIEN 324 TW

## T101G30

Polyethylene Terephthalate (PET), glass reinforced, furnished as pellets

	Min Thk	Flame			RTI	RTI	RTI
Color	(mm)	Class	HWI	HAI	Elec	Imp	Str
ALL	0.71	HB	3	0	140	130	140
	1.5	HB	1	1	140	140	140
	3.0	HB	1	1	140	140	150
Comparative	e Tracking Index (CT	I): <b>2</b>	Inclined Plane Tracking (IPT): -				-
Dielec	tric Strength (kV/mm	ו): <b>25</b>		Volume Re	sistivity (10 <sup>x</sup>	ohm-cm) :	16
High-Volt	age Arc Tracking Ra (HVTF)	te R): <b>2</b>	High Volt, Low Current Arc Resis (D495): 5				
Dim	nensional Stability (%	b): 0					
ANSI/11 04 om	all scale test data dee	a not portain to bui	ildina motorial	o furniching	a and related	contonto AN	

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1987-07-14

Last Revised: 2010-01-15

© 2013 UL LLC



## **IEC and ISO Test Methods**

Test Name Flammability	Test Method IEC 60695-11-10	Units Class (color)	Thickness Tested (mm) 0.71 1.5 3.0	Value HB75 (ALL) HB75 (ALL) HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	С	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	С	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	С	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	С	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m <sup>2</sup>	-	-
ISO Izod Impact	ISO 180	kJ/m <sup>2</sup>	-	-
ISO Charpy Impact	ISO 179-2	kJ/m <sup>2</sup>	-	-

## © 2013 UL LLC

The materials covered in this database are incomplete in certain constructional features or restricted in performance capabilities and are intended for use as components of complete equipment submitted for investigation rather than for direct separate installation in the field. THE FINAL ACCEPTANCE OF THE COMPONENT IS DEPENDENT UPON ITS INSTALLATION AND USE IN COMPLETE PRODUCTS SUBMITTED TO UNDERWRITERS LABORATORIES.

Notice of Disclaimer