

iq.ul.com

Component - Plastics [\[guide info\]](#)

E59481

CHANG CHUN PLASTICS CO LTD

7TH FL, 301 SONGKIANG RD, TAIPEI 104 TW

T375HF

Phenolic Molding Compound (PMC), "LONGLITE", furnished as pellets, granular material, or powder

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
BK	0.43	V-0	0	0	150	150	150
	0.75	V-0	0	0	150	150	150
	3.2	V-0	0	0	150	150	150

Comparative Tracking Index (CTI): 3

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): 10

Volume Resistivity (10^x ohm-cm): 11

High-Voltage Arc Tracking Rate (HVTR): 3

High Volt, Low Current Arc Resis (D495): 4

Dimensional Stability (%): -

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2006-03-29

Last Revised: 2014-03-21

© 2016 UL LLC



IEC and ISO Test Methods

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	0.43	V-0 (BK)
			0.75	V-0 (BK)
			3.2	V-0 (BK)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	3.2	960
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	3.2	960
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	3.0	190
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-